

Glass nonwovens

Material Specification

WOVEN ROVING B9715-100-100 B3-290

is produced of continuous basalt fiber under quality system conforming to ISO 9001 and to the requirements of ISO 2113.

Raw materials

ver 1 Petro Huoponen

Element	Warp	Weft					
Nominal weight g/m ²	145	145					
Tex	270	270					
Type of yarn	Basalt	Basalt					
Ends / 10cm	50	52					
Notice	Compatible with polyester, vinyl ester and epoxy resins.						

Product

Standard elements	Weight						
Nominal value	290 g/m ²						
Tolerance	± 5 %						
Test method	ISO 3374						
Notice							
Custom elements	Weave Pattern						
Value	Plain						
Notice							

Delivery	
Customer	
Address	
Order no.	
Delivery number	
Quantity	
Batch codes	
Notice	

STORAGE: The product should be stored in its original packaging in a dry, cool environment. If the product is stored at a temperature below +15°C conditioning in the workshop is recommended for at least 24 hours. It is recommended that the product is used within 12 months of delivery.

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom deems appropriate. Refer to www.ahlstrom.com for contact information.

Mikkeli
26.10.2007

SIGNATURE: Petro Huoponen

Small fibers. Big difference.

