FiberComposites

Material Specification woven ROVING 9715-125-100 R6-300

is produced of continuous E-glass under quality system conforming to ISO 9001 and to the requirements of ISO 2113.

Raw materials ver 2 Minna Venalainen

Element	Warp	Weft				
Tex (ISO 1889)	300 ± 10 %	600 ± 10 %				
Type of yarn	EC 300	EC 600				
Ends / 10cm (ISO 4602)	48 ± 5 %	25 ± 5 %				
Notice	Compatible with polyester, vinyl ester and epoxy resins.					

Product

Standard elements	Inner core type				
Nominal value	Ø 76 x 3,5 mm				
Notice					
Custom elements	Type of weave	Ratio			
Value	Plain	48/52			
Notice					

Delivery				
Customer				
Address				
Order no.				
Delivery number				
Quantity				
Batch codes				
Notice				

STORAGE: The product should be stored in its original packaging in a dry, cool environment. If the product is stored at a temperature below +15°C conditioning in the workshop is recommended for at least 24 hours. It is recommended that the product is used within 12 months of delivery.

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom deems appropriate. Refer to www.ahlstrom.com for contact information.

Mikkeli 19.7.2005

